

Product Description

Deze eigendomsetiketten vallen uiteen bij poging tot verwijderen.
Door de eierschaalstructuur en de sterk hechtende lijm versnipperen deze in kleine stukjes bij het verwijderen.

U kan de eigendomsetiketten gebruiken voor:

- Werkplekbeheer
- Productieproces
- Voorraadbeheer
- Eigendomsregistratie
- Onderhoudsbeheer



Material specifications

Description

Facefilm: 60 micron, brittle, matt white, cast vinyl film
Adhesive: permanent, acrylic based
Backing paper: one side coated white kraft paper, 140 g/m²

Temperature range

Features Results
Minimum application temperature +10° C
Service temperature: - 50° to +110° C

Physical properties

Features	Test method	Results
Caliper, facefilm	ISO 534	60 micron
Tensile strength	DIN 53455	1,0 kN/m
Elongation	DIN 53455	10 %
Dimensional stability	DIN 30646	0,2 mm max.
Adhesion, initial	FINAT FTM-1, stainless steel	600 N/m
Adhesion, ultimate	FINAT FTM-1, stainless steel	800 N/m
Flammability		Self extinguishing
Shelf life	Stored at 22° C/50-55 % RH	2 years
Durability	Vertical exposure	5 years

Temperature range

Features	Results
Minimum application temperature	+10° C
Service temperature:	- 50° to +110° C

Chemical properties

Features	Test method	Results
Humidity resistance	120 hours exposure	No effect
Corrosion resistance	120 hours exposure	No contribution to corrosion
Water resistance	48 hours immersion	No effect
Chemical resistance	48 hours immersion	No effect
Solvent resistance	Applied to aluminium, exposed to: oils, greases, aliphatic solvents, motor oils, heptane, kerosene and JP-4 fuel.	No effect

Eigenschappen Destructible eigendomsetiketten:

- Full color (CMYK digitale print)
- Permanente acryllijm voor gebruik bij temperaturen tussen -50°C en +110°C
- Voor gebogen en vlakke ondergronden
- Leverbaar in mat wit
- Gratis samples op maat (geheel vrijblijvend)
- Niet te lamineren (i.v.m. zelfvernietigende eigenschappen)

De etiketten worden, ter voorkoming van dubbelvouwen, geleverd in een koker met daarbij een spuitbus Surface Cleaner voor het reinigen van de ondergrond.