

**Product Data Sheet:** 

## **EPWR GREASE NLGI 2.5**

**Product Description:** 

**EPWR GREASE NLGI 2.5** is a lithium-calcium thickened lubricating grease based on mineral oil.

**EPWR GREASE NLGI 2.5** contains antioxidants, corrosion inhibitors and EP/AW additives. The thickener, together with the base oil, makes **EPWR GREASE NLGI 2.5** suitable for the lubrication of slow moving and heavily loaded bearings.

**EPWR GREASE NLGI 2.5** has excellent water resistance, good load carrying capacity and endures high shock loads.

**EPWR GREASE NLGI 2.5** is suitable for heavily loaded agricultural & industrial applications where water wash is problematic.

**EPWR GREASE NLGI 2.5** is also suitable for heavy-duty vehicles working outdoors in wet and dirty conditions.

| Property:                       |                         | Test Method:                | <b>Typical Values:</b> |
|---------------------------------|-------------------------|-----------------------------|------------------------|
| Classification:                 |                         | DIN 51502                   | KP2.5K-20              |
|                                 |                         | <b>ISO 6743</b>             | ISO-L-XBCHB2.5         |
| NLGI Grade                      |                         | ASTM D217                   | 2.5                    |
| Base Oil Viscosity @ 40°C       |                         | ISO 12058                   | 465 mm <sup>2</sup> /s |
| Base Oil Viscosity @ 100°C      |                         | <b>ISO 12058</b>            | 27 mm²/s               |
| Colour                          |                         | Visual                      | Brown                  |
| Dropping Point                  |                         | IP 396                      | >180°C                 |
| Approximate Density @ 20°C      |                         | IPPM-CS/03                  | 920 kg/m <sup>3</sup>  |
| 4-Ball weld load                |                         | DIN 51350-4                 | 3200 N                 |
| <b>Temperature Range</b>        |                         |                             |                        |
| Continuous operation:           |                         | -                           | -20°C to +120°C        |
| Maximum short period:           |                         | -                           | +130°C                 |
| Penetration 60 strokes:         |                         | ISO 2137                    | 245-275                |
| Penetration 100 strokes:        |                         | ISO 2137                    | +40                    |
| SKF Emcor WWO distilled water   |                         | ISO 11007mod                | 2-2                    |
| Copper Corrosion 24 hrs @ 100°C |                         | <b>ASTM D4048</b>           | 1b                     |
| Oil Separation 168 hrs @ 40°C   |                         | IP 121                      | 3%                     |
| Water resistance                |                         | DIN 51807-1                 | 1-90                   |
| 4-ball wear scar 1 hr @ 400 N   |                         | DIN 51350-5                 | 0.7 mm                 |
| Flow pressure @ -35°C           |                         | DIN 51805                   | <1400 hPa              |
|                                 |                         |                             |                        |
| Product nr: 4405                | Date Issued: 22/10/2011 | Date Superseded: 17/07/2010 | Revision nr: 01        |