

# Blockout BLM 600SM Proficoat Series

#### **Ikonos Proficoat Blockout BLM 600SM**

#### → PRODUCT DESCRIPTION

Economical version of blockout, which consist of two layers of PP intentionally laminated with black adhesive in order to block the light from both sides with white back. Perfect for roll-up and POS application.

#### → AVAILABLE STANDARD WIDTHS AND LENGTHS

0.91, 1.10, 1.27 x 30 m. Other lengths on Customers' individual request

#### → PRODUCT STRUCTURE

Base material: Polypropylene 80 mic + black blocker + polypropylene 80 mic

Ink receptive coating: 25 mic (+/- 2 mic)

Total: 185 mic

### → SURFACE

SFMI-MATT

#### → COMPATIBLE INKS

ECO-SOLVENT / MILD SOLVENT / SOLVENT / UV / LATEX

## → PRINTABLE SIDE

OUTSIDE

#### → PHYSICAL FEATURES

	STANDARD NO.	VALUE
Weight (Total) [gsm]	ISO 536	132
Thickness (total) [microns]	ISO 534	150 mic
thickness of PP		2x 80 mic
thickness of ink receptive coating		25 mic

After printing the ink must be perfectly dry so as to avoid any affect on the later combination with the application surface. The surface on which material is applied must be free of dust, grease, lubricant and any other substances which may hinder the film from adhesion. Freshly lacquered or painted surfaces should be allowed to dry for no less than three weeks. The compatibility of particular lacquers and points should be tested by the user, prior to application on the material.

All rights reserved. All trademarks and registered trademarks are the property of their respective owners. The information included in the present publication is based upon our knowledge as well as practical experience and can be changed without prior notice. This data is displayed only in order to serve as a source of information and is given without guarantee and does not constitute a warranty. Owing to wide range of possible uses and applications, customers should independently verify the appropriateness of this material for their explicit purpose, prior to use.

IKONOS LARGE FORMAT PRINTING MEDIA Polska, 45-446 Opole, ul. Gosławicka 2D Tel.: +48 77 455 63 19 / Fax: +48 77 455 63 17